












### Standard Stock Colors

				
<b>Regal White</b> SR: .68 IE: .86 SRI: 82	<b>Bone White</b> SR: .72 IE: .84 SRI: 87	<b>Almond</b> SR: .63 IE: .86 SRI: 75	<b>Sandstone</b> SR: .54 IE: .86 SRI: 63	<b>Medium Bronze</b> SR: .30 IE: .87 SRI: 31
				
<b>Dark Bronze</b> SR: .26 IE: .84 SRI: 24	<b>Dove Grey</b> SR: .49 IE: .87 SRI: 56	<b>Slate Gray</b> SR: .37 IE: .86 SRI: 39	<b>Charcoal</b> SR: .32 IE: .85 SRI: 32	<b>Matte Black</b> SR: .27 IE: .86 SRI: 26
				
<b>Slate Blue</b> SR: .26 IE: .85 SRI: 24	<b>Patina Green</b> SR: .29 IE: .87 SRI: 29	<b>Classic Green</b> SR: .26 IE: .84 SRI: 24	<b>Bright Silver Mica**</b> SR: .60 IE: .77 SRI: 68	

### Standard Non-Stock Colors

				
<b>Sierra Tan</b> SR: .35 IE: .86 SRI: 37	<b>Surrey Beige</b> SR: .40 IE: .86 SRI: 43	<b>Mansard Brown</b> SR: .29 IE: .86 SRI: 29	<b>Hemlock Green</b> SR: .28 IE: .87 SRI: 28	<b>Hartford Green*</b> SR: .10 IE: .82 SRI: 2
				
<b>Regal Blue*</b> SR: .28 IE: .86 SRI: 27	<b>Banner Red^^</b> SR: .42 IE: .84 SRI: 45	<b>Colonial Red</b> SR: .34 IE: .86 SRI: 35	<b>Silversmith**</b> SR: .53 IE: .78 SRI: 59	<b>Champagne^^**</b> SR: .37 IE: .83 SRI: 38
				
<b>Pewter**</b> SR: .36 IE: .85 SRI: 38				

SR = Solar Reflectivity  
IE = Initial Emissivity  
SRI = Solar Reflective Index

\* Denotes Dark Colors ^^ Denotes Exotic Colors \*\* Features a pearlescent mica finish; subject to premium pricing.

Colors shown are as close to actual colors as allowed by the printing process. Actual metalsamples are available. Colors may appear different when viewed at different angles and under different lighting conditions. Due to product improvements, changes and other factors, we reserve the right to change or delete information herein without prior notice.

ARCHITECTURAL PVDF				STEEL (GA)				ALUMINUM (in)	
FABRAL COLOR	SR	IE	SRI	24GA	24GA	24GA	22GA	.032	.040
Standard Coil Width				48.375"	43"	44.375"	44.375"	48.250"	48.250"
STANDARD STOCK COLORS	Regal White	.68	.86	82	✓	✓	✓	✓	✓
	Bone White	.72	.84	87	✓	✓	✓	✓	✓
	Almond	.63	.86	75	✓	✓	✓	✓	✓
	Sandstone	.54	.86	63	✓	✓	✓	✓	✓
	Medium Bronze	.30	.87	31	✓	✓	✓	✓	✓
	Dark Bronze	.26	.84	24	✓	✓	✓	✓	✓
	Dove Grey	.49	.87	56	✓	✓	✓	✓	✓
	Slate Gray	.37	.86	39	✓	✓	✓	✓	✓
	Charcoal	.32	.85	32	✓	✓	✓	✓	✓
	Matte Black	.27	.86	26	✓	✓	✓	✓	✓
	Slate Blue	.26	.85	24	✓	✓	✓	✓	✓
	Patina Green	.29	.87	29	✓	✓	✓	✓	✓
	Classic Green	.26	.84	24	✓	✓	✓	✓	✓
	Bright Silver **	.60	.77	68	✓	✓	✓	✓	✓
Bare Galvalume	N/A	N/A	N/A	✓	✓	✓	✓	✓	
STANDARD NON-STOCK COLORS	Sierra Tan	.35	.86	37					
	Surrey Beige	.40	.86	43					
	Mansard Brown	.29	.86	29					
	Hemlock Green	.28	.87	28					
	Hartford Green*	.10	.82	2					
	Regal Blue*	.28	.86	27					
	Banner Red^^	.42	.84	45					
	Colonial Red	.34	.86	35					
	Silversmith**	.53	.78	59					
	Champagne^^ **	.37	.83	38					
Pewter**	.36	.85	38						

PAINT PERFORMANCE PROPERTIES	HOT-DIPPED GALVANIZED STEEL OR GALVALUME®	ALUMINUM
Accelerated Weathering ASTM D 4587 (Drew Cycle Weatherometer) ASTM G 23	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max	Hours: 3,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max Hours: 5,000 Total Chalk: Rating 8 Color: 5 Δ E Hunter units max
Salt Spray ASTM B 117	Hours: 1,000 Total Scribe: Rating 7 1/8" (1.6mm) Field: Rating 10, no blisters	Hours: 3,000 Total Scribe: Rating 10, no creepage Field: Rating 10, no blisters
Humidity ASTM D 2247	Hours: 2,000 Total Rating: 10, No blisters	Hours: 3,000 Total Rating: 10, No blisters
Formability ASTM D 4145	0T-3T	0T-3T
ASTM D 522 (Elongation over 1/8" mandrel)	No cracking No loss of adhesion	No cracking No loss of adhesion
Pencil Hardness ASTM D 3363	HB-2H	HB-2H
Abrasion Resistance ASTM D 968	55-75 Liters of falling sand	55-75 Liters of falling sand
Specular Gloss ASTM D 523	20-35 at 60°	20-35 at 60°
Reverse Impact ASTM D 2794	2x Metal thickness in inch-lbs No loss of adhesion	1 1/2x Metal thickness in inch-lbs No loss of adhesion
Flame Test ASTM E 84	Class A-rated coating	Class A-rated coating

✓ Stocked Color

\* Denotes Dark Colors

^^ Denotes Exotic Colors

\*\* Features a pearlescent mica finish; subject to premium pricing

**NOTES ON AVAILABILITY:**

- For availability on products, colors, gauges and coil widths, please contact your Fabral Sales Representative.
- Standard inventory is non-embossed. Please contact us for the availability of stucco embossing.
- Protective, strippable film is available upon request.
- Mica colors are subject to premium pricing. Due to the unique effect of the Mica finishes, appearances may vary from batch to batch.
- Bare Galvalume, special paint systems and coating systems are available. Please contact your Fabral Sales Representative for details.
- All colors are supplied in Medium Gloss (20-35 at 60°). Low Gloss available and subject to minimum coating run.
- Subject to change without notice.
- Fabral standard architectural colors and finishes feature 70% polyvinylidene fluoride (PVDF) resin paint systems to ensure long-term color retention and performance. Custom colors and finishes are also available. Minimum quantities and set-up charges may apply.
- Order Minimums: Non-stock standard color orders must meet minimum coating requirements. Please contact your Fabral Sales Representative

Due to product improvements, changes and other factors, we reserve the right to change or delete information herein without prior notice.